



parLiner

- › Testliner 3
- › Light weight
- › 100% recycled fibres
- › FSC Certified

Grammage	Burst	Burstindex	SCT CD	Dennison
<i>ISO 536</i>	<i>ISO2759</i>		<i>ISO 9895</i>	<i>TAPPI</i>
<i>+/- 3%</i>	<i>+/- 10%</i>		<i>+/- 10%</i>	<i>UM-459</i>
70	147	2,10	1,09	> 14
80	168	2,10	1,36	> 14
90	212	2,36	1,60	> 14
100	242	2,42	1,83	> 16
110	251	2,45	1,97	> 16
120	277	2,40	2,15	> 16
125	288	2,38	2,20	> 16
130	300	2,37	2,31	> 16
135	309	2,44	2,42	> 16
140	345	2,46	2,47	> 16

Cobb 60	Internal Scottbond	Roughness	Moisture
ISO 535		ISO 8791-2	ISO 287
35 – 40	>180 J/m	1550 ml/min	7,5% +/- 1